

Cemef

July, 9th 2018, Saint-Malo, France

Nucleated bubbles in glass former liquids undergoing coalescence and growth

D. Boloré (Surface du Verre et Interfaces, UMR 125 CNRS/Saint-Gobain) & F. Pigeonneau

Industrial Context

Cullet is mainly used for the production of container glass:

Germany	88 %	Belgium	95 %	France	73 %
Poland	<mark>43</mark> %	Italy	76 %	Austria	93 %
United-Kingdom	64 %	Portugal	60 %	Spain	60 %
Sweden	<mark>97</mark> %	Holland	79 %	Denmark	<mark>98</mark> %

Table 1: Rates of glass recycling in Europe in 2013 [data SEVE].

- Advantages of introduction of cullet in raw materials:
 - Reductions of mineral resources;
 - Reduction of CO₂ release;
 - Reduction of the energy to provide.



Industrial Context

Cullet is mainly used for the production of container glass:

Germany	88 %	Belgium	95 %	France	73 %
Poland	<mark>43</mark> %	Italy	76 %	Austria	93 %
United-Kingdom	64 %	Portugal	60 %	Spain	60 %
Sweden	<mark>97</mark> %	Holland	79 %	Denmark	<mark>98</mark> %

Table 1: Rates of glass recycling in Europe in 2013 [data SEVE].

- Advantages of introduction of cullet in raw materials:
 - Reductions of mineral resources;
 - Reduction of CO₂ release;
 - Reduction of the energy to provide.

What is the limitation to go forward 100 % of cullet?

Ceme



- 1. Experimental set-up
- 2. Spatial distributions of nucleated bubbles
- 3. Bubble growth rate
- 4. Saturation and nucleation
- 5. Conclusion

1. Experimental set-up





- Float glass samples are introduced in silica crucible;
- Recording of the melting and other events with 2 cameras (60 and 25 µm/px).

Figure 1: Sketch of HTO furnace.

SiO₂ Al_2O_3 SO_3 FeO Na₂O CaO MgO Fe₂O₃ 72.4 13.85 8.88 374 0.73 0.22 0.055 0.014 Table 2: Composition of the glass samples (wt %).

2. Spatial distributions of nucleated bubbles





2. Spatial distributions of nucleated bubbles





Figure 2: Detection of nucleation sites on each face of the crucible and Voronoï diagram of nucleation sites.

2. Spatial distributions of nucleated bubbles





$$f(x) = n^{n} x^{n-1} e^{-nx} / \Gamma(n), \quad (1)$$

with $x = \frac{A}{\langle A \rangle}.$

• Atmosphere side: n = 3.5; Tin side: n = 12.2 at the beginning and n = 25.5 at the end.

Figure 3: PDF of the area of Voronoï cells.

For objects randomly distributed over a surface, $n = 7/2^{1}$. ¹Ferenc, J.-S. & Néda, Z. (2007). *Physica A*, **385**:518–526

2. Spatial distributions of nucleated bubbles 🖉





Figure 4: PDF of area of Voronoï cells obtained from the numerical simulations.

2. Spatial distributions of nucleated bubbles 🖉



Cemef



Figure 5: *n* vs. the proportion of coalesced objects.

$$n = \frac{7}{2}e^{2.47x}$$
, with $x = \frac{d_0 - d}{d_0}$. (2)

2. Spatial distributions of nucleated bubbles 🖉





Figure 6: Bubble densities on the two sides of glass samples.

- ► In atmosphere side, $d_0 = 40$ nuclei/cm²;
- ▶ In tin side, $d_0 = 9300$ nuclei/cm² (230 times larger).

3. Bubble growth rate



Figure 7: $a (\mu m)$ vs. $\sqrt{t} (\sqrt{s})$ for bubbles in tin and atmosphere sides of molten glass samples.



3. Bubble growth rate



Figure 7: $a (\mu m)$ vs. $\sqrt{t} (\sqrt{s})$ for bubbles on tin and atmosphere sides of molten glass samples.





3. Bubble growth rate

In the mass transfer modeling, we consider two redox couples²:

$$Fe^{3+} + \frac{1}{2}O^{2-} \rightleftharpoons Fe^{2+} + \frac{1}{4}O_2,$$

$$Sn^{4+} + O^{2-} \rightleftharpoons Sn^{2+} + \frac{1}{2}O_2.$$
(3)
(4)

- ► Using the experimental bubble growth rate, the "equilibrium" P_{O₂} is:
 - In atmosphere side, $P_{O_2} = 1.3 \cdot 10^{-3}$ Pa;
 - In tin side, $P_{O_2} = 4.1 \cdot 10^{-4}$ Pa.
- Tin leads to a reduction of glass.

²Pigeonneau, F. (2011). Int. J. Heat Mass Transfer, **54**:1448-1455.



4. Saturation and nucleation

 The critical bubble size for nucleation in the case of multi-species is given by

$$a_{\rm cr} = \frac{2\gamma}{\left(\sum_{i=1}^{N_g} Sa_{G_i}^{1/\beta_{G_i}} - 1\right)P_l},$$

$$Sa_{G_i} = \frac{C_{G_i}}{L_{G_i}P_l^{\beta_{G_i}}}.$$
(6)

• The supersaturation for N_g dissolved species is

$$\sigma = \sum_{i=1}^{N_g} Sa_{G_i}^{1/\beta_{G_i}} - 1.$$
 (7)





4. Saturation and nucleation



Figure 8: σ vs. T (°C) in atmosphere and tin sides.





- Remelting of cullet leads to a large bubble formation.
- Enhancements of the bubble nucleation and growth rate due to the tin pollution.
- The glass reduction on tin side is the main parameter controlling the bubble nucleation and the growth rate.
- Difficult to quantify the bubble nucleation rate (work in progress to improve the prediction).
- The 100 % of cullet is difficult to reach because the bubble creation persists and needs to introduce fining agents.
- See for more details³.

³Boloré, D. & Pigeonneau, F. (2018). J. Am. Ceram. Soc., 101:1892-1905.